

# decotric Contact Adhesive

## decotric Kontakkleber

### Solvent-free contact adhesive for bonding cork floor tiles

**Instructions for use:** *decotric Contact Adhesive* is suitable for glueing cork floor tiles without back coating onto absorbent and non-absorbent, even, level surfaces. Suitable for floor heating.  
PVC coverings are not suitable as surfaces.

**Technical specification:**

Components:	Natural latex, plastic dispersion
Density:	approx. 1.00 g/cm <sup>3</sup>
pH value:	approx. 8
Consumption:	approx. 250 g/m <sup>2</sup>

**Surface preparation:** The surface must be stable, dry and even. Prime strongly absorbent and sanding surfaces with *decotric Deeply Penetrating Primer - solvent free*. Sweep off dusty surfaces and pretreat with *decotric Deeply Penetrating Primer - solvent free* too. Level rough and uneven screeds with *AKAPLAN Floor Levelling Compound* or *AKAFLEX Floor Levelling Compound*.

Sealed wooden floors and surfaces of other subfloors should be cleaned by an appropriate cleaning agent.

**Application:** The cork plates to be bonded should be stored in the installation room approx. 24 hours before the laying job. Coat the cork plates and the surface to be bonded evenly with *decotric Contact Adhesive* and allow to flash off completely. We recommend using a short-piled roller or brush to process the *decotric Contact Adhesive*.

Coating of the cork floor tiles can take place already one day before laying the tiles and, when the adhesive has completely flashed off, the tiles can be stacked (ensure dustlessness). The surface must always be coated just before the laying work.

The coated cork plates must be immediately laid once the applied adhesive has flashed off. For this purpose, place the cork plates onto the coated surface allowing for an exact fit, press them firmly on and fasten them firmly with a rubber mallet particularly in the boundary region. The cork plates should be exactly laid onto the glue because they cannot be displaced any longer after contact of the two adhesive films.

The laid cork coverings are immediately walkable. Surface treatment should commence after 24 hours at the earliest. The laying instructions of the cork floor covering manufacturers must be complied with.

Do not process below +15 °C object and room temperature as well as above 75 % rel. humidity. Clean any working equipment with water immediately after use.

**Storage:** Keep cool but protected from frost! Keep container tightly sealed!

**Available size:** 2.5 kg 007302001